



INDUSTRIAL TECHNOLOGY INSTITUTE (ITI)

P. O. Box, 787, 363, Bauddhaloka Mawatha, Colombo 7, Sri Lanka.

Telephone: +94 11 2379800 Fax: +94 11 2379850

120/4A, Vidya Mawatha, Colombo 7, Sri Lanka.

Telephone: +94 11 2379800 Fax: +94 11 2379950

503/A, Halbarawa Gardens, Thalahena, Malambe, Sri Lanka.

Telephone: +94 11 2797300 Fax: +94 11 2379848

TEST REPORT

Report No. CTS 1817249

Report to :

GB Coatings (Pvt) Ltd.,
468/1B, Ranasinghe Mawatha,
Mullariyawa.

Issued By :


Materials Laboratory,
Industrial Technology Institute,
363, Bauddhaloka Mawatha,
Colombo 07.

2018-11-05

Page 01 of 04 Pages

THE REPORT IS ISSUED SUBJECT TO CONDITIONS MENTIONED OVERLEAF

"PLEASE ADDRESS ALL COVERS TO THE DIRECTOR GENERAL"



TEST REPORT

Report No. - CTS 1817249

Customer : GB Coatings (Pvt) Ltd., 468/1B, Ranasinghe Mawatha, Mullariyawa.	Test Item : Paint, Wall filler, Skim coat Service Requested : Customer's letter dated 2018-10-08
Description : Three (03) test items.	Identification of Test Item : Test items were labelled as; 1. Sample Solakro Paints GB Coatings (Pvt) Ltd., No. 700/10, Kaduwela Rd, Thalangama North, Battaramulla. 2. Dulux ACRYLIC Wall Filler MFD : AUG 2018 Best Before : 31-07-2020 B 20180701 1 L 3. Dulux Pure Brilliant White MFD : MAR 2018 Best Before : 28-02-2023 B 20180301 1 L Date of receipt of test item : 2018-10-08
Test Dates : From 2018-10-15 to 2018-11-02	



... Continuation Sheet

Report No. - CTS 1817249

TEST RESULTS :

Test / Unit	Test method	Results
1. Surface cracks	Customer's method	No
2. Peel off		No
3. Other surface imperfection		No

Test Method :


1. Two coatings of skim coat were applied on top of a cement base substrate and kept for 24 hours for drying. Then a coating of wall filler was applied on it and kept for six hours for drying.
2. The first coating of emulsion paint was applied on the wall filler surface and after 24 hours, the second coat was applied with the same paint.
3. Visually observed for surface cracks, peel off and any other surface imperfection during one week period of time.


Authorized Signatory

A.A.M.T. Adikari
Research Engineer
Materials Laboratory

2018-11-05

-/SS.


Shashikala Liyanage
Assistant Research Technologist

Page 04 of 04 pages